

EXCEL MAPLITHO

S.NO	PARAMETERS	UNIT	50/60 GSM	68/70 GSM	80 GSM
1	Substance	g/m ²	2.5%	2.5%	2.5%
2	Bulk	cc/gm	1.25 - 1.26	1.25 - 1.27	1.25 - 1.27
3	Brightness	%	84±1	84±1	84±1
4	Opacity	%	84.0 min	85.0 min	86.0 min
5	Smoothness				
	T/S	ml/min	80/100	80/100	100/140
	W/S	ml/min	100/120	100/120	160/200
6	Porosity	ml/min	60/100	60/100	60/100
7	Breaking Length (Min)				
	MD	meters	3800±200	3800±200	3800±200
	CD	meters	2000±200	2000±200	2000±200
8	Tear Factor				
	MD	-	50±5	50±5	50±5
	CD	-	60±5	60±5	60±5
9	Sizing (Cobb 60)	gsm	25±2	25±2	25±2
10	Passed Wax Pick No	No.	11A	11A	11A